



Dimension board

LENGTH	1900 mm
WIDTH	190 mm
TOTAL THICKNESS	14 mm
THICKNESS TOP LAYER	3 mm
LAYER CONTENTS	Min 6 Pl x 1900 mm

Dimension pack

PACK LENGTH	1950 mm
PACK WIDTH	200 mm
PACK THICKNESS	120 mm
PACK WEIGHT	23 kg
LAYERS/BOX	8
M²/PACK	2.89 m ²

Dimension pallet

PALLET LENGTH	1950 mm
PALLET WIDTH	1000 mm
PALLET HEIGHT	1080 mm
PALLET WEIGHT	960 kg
PACKS/PALLET	40
M²/PALLET	115.60 m ²

CHARACTERISTICS

Top layer

WOOD SPECIES	Oak
LATIN NAME	Quercus Robur
GRADE	ABC
CONSTRUCTION	3-layer
THICKNESS TOP LAYER	3 mm
PATTERN	1 strip
CUTTING METHOD	Zaagfineer
BEVEL	Bevel 2 long sides 0,75 mm
FINISH	Oil
SURFACE STRUCTURE	Smooth

Composition of the support

SUPPORT TYPE	Populier
WOOD SPECIES SUPPORT	Populier
TOTAL THICKNESS SUPPORT	11 mm
ADHESION	Kruiselings

Installation

SYSTEM	APPLICATIONS	UNDERFLOOR HEATING
Tongue and groove	Licht huishoudelijk gebruik. Matig commercieel gebruik. Neem de nodige maatregelen voor gebruik in vochtige ruimtes. Normaal commercieel gebruik. Normaal huishoudelijk gebruik. Overvloedig commercieel gebruik.	Yes
		RE-SANDABLE
		Yes

CERTIFICATION

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1
- Does not contain any PCP (pentachlorophenol)

TECHNICAL SPECIFICATIONS

- Hardness: N / mm² (Birrell Hardness) 3.40
- Thermal conductivity: 14,00 (W / (mK)) R = 0.11 m² K / W

Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)